

PRODUCT INFORMATION



SOLID[®] BLOCKBOARD

SOLID Laminboard Core 3 Layers

Deck	rotary cut veneer, HDF or chipboard
Core	3-5 mm strips of spruce or light wood
Veneer types	fromager, poplar, beech
Glue	IF 20; AW 100 available on request
Emission class	E1; E0 on request
Format	2070 x 2600/5200 mm 1250 x 2500 mm
Thickness	16/18/19/22/25/28/38 mm other thicknesses are available on request
Max. press format	2200 x 6300 mm
Moisture content	8 – 12%
Thickness tolerance	+ 0,2 mm – 0,6 mm
Tolerance in length and width	± 2 mm/m
Squareness tolerance	1 mm/m

Thickness in mm	E-Modul (N/mm ²) (length)	E-Modul (N/mm ²) (width)	Bending strength (N/mm ²) (length)	Bending strength (N/mm ²) (width)
16	2000	5400	20	45
18				
19	1500	6000	15	50
22	1400	6700	15	50
25	1300	7100	15	50
28				
38				

Multiple applications

HS Baco Panels offers the most suitable blockboard for each application.

A wide range of surface and cores ensure various alternatives. Additionally we develop solutions together with our customers, according to their individual requirements.

Significant advantages

- High stability and moisture resistance
- High bending strength
- Light weight
- High screw extraction resistance
- Easy processing

High quality

High quality raw material and longtime experience of our team are the basis for the outstanding quality of our blockboards.

Continuous quality controls ensure stable standards.

All wood that is processed by HS Baco Panels comes from PEFC™ controlled sources.

HS Baco Panels S.R.L.
Strada Crinului nr. 15, 605200 Comănești, România
T: +40 234 374 052
F: +40 234 374 622

baco.sales@hs.ro
www.hs.ro
www.hs.at